



MegaSol: Natural Gypsum Screenings

Product Code 670

TYPICAL CHEMICAL ANALYSIS

Chemical Compound		% of Sample
Gypsum	CaSO ₄ 2H ₂ O	87
Elemental Calcium	Ca	20
Elemental Sulfur	S	16
Carbonate	CaCO ₃ /MgCO ₃	8

AVERAGE PARTICLE SIZE DISTRIBUTION

U.S. Mesh Screen	% Retained	% Passing
4	13	87
8	11	76
20	11	65
60	19	46
Pan	46	

Typical Moisture: 3-6%

Sourced in the U.S.